



IFW

Attorney Docket No. 9286.32

PATENT

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re: Tsai et al.

Confirmation No. 2750

Application Serial No.: 10/780,781

Filed: February 18, 2004

For: *Process for Preparing an Elastic Nonwoven Web*

Date: June 30, 2004

Commissioner for Patents

P.O. Box 1450

Alexandria, VA 22313-1450

SUBMITTAL OF PRIORITY DOCUMENT

Sir:

To complete the requirements of 35 U.S.C. § 119, enclosed is a certified copy of European priority Application No. 03028126.5 filed May 12, 2003.

If any extension of time for the accompanying response or submission is required, Applicant requests that this be considered a petition therefor. No fee is believed due, however, the Commissioner is hereby authorized to charge any deficiency, or credit any refund, to our Deposit Account No. 50-0220.

Respectfully submitted,

Mary L. Miller

Registration No. 39,303

Myers Bigel Sibley & Sajovec

PO Box 37428

Raleigh NC 27627


Tel (919) 854-1400

Fax (919) 854-1401

Certificate of Mailing under 37 CFR 1.8

I hereby certify that this correspondence is being deposited with the United States Postal Service with sufficient postage as first class mail in an envelope addressed to: Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450, on June 30, 2004.

Cathy A. Schetzina





**Europäisches
Patentamt**

**European
Patent Office**

**Office européen
des brevets**

Bescheinigung

Certificate

Attestation

Die angehefteten Unterlagen stimmen mit der ursprünglich eingereichten Fassung der auf dem nächsten Blatt bezeichneten europäischen Patentanmeldung überein.

The attached documents are exact copies of the European patent application described on the following page, as originally filed.

Les documents fixés à cette attestation sont conformes à la version initialement déposée de la demande de brevet européen spécifiée à la page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

03028126.5

Der Präsident des Europäischen Patentamts;
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

R C van Dijk



Anmeldung Nr:
Application no.: 03028126.5
Demande no:

Anmeldetag:
Date of filing: 05.12.03
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

Phoenix Intellectuals and Technologies
Management, Inc.
6, Lane 213,
Sec. 1, Hai-Den Road
Tainan 709
TAIWAN

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.
If no title is shown please refer to the description.
Si aucun titre n'est indiqué se référer à la description.)

Process for preparing an elastic nonwoven web

In Anspruch genommene Priorität(en) / Priority(ies) claimed /Priorité(s)
revendiquée(s)
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/
Classification internationale des brevets:

D04H/

Am Anmeldetag benannte Vertragstaaten/Contracting states designated at date of
filing/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IT LU MC NL
PT RO SE SI SK TR LI

PROCESS FOR PREPARING AN ELASTIC NONWOVEN WEB ^{EPO - Munich}
33

05. Dez. 2003

FIELD OF THE INVENTION

The present invention relates to a process for preparing an elastic thermally bonded nonwoven web or fiber mat and an elastic thermally bonded nonwoven web or fiber mat prepared by the process according to the invention. The present invention also relates to the use of the elastic thermally bonded nonwoven web or fiber mat prepared according to the invention in the manufacture of a disposable sanitary protection product, a medical product, a protective work-wear or a personal use item. Finally, the present invention relates to a product containing the elastic nonwoven web or fiber mat of the invention.

BACKGROUND OF THE INVENTION

Thermally bonded nonwoven webs are well known in the art (Wendt, Industrial and Engineering Chemistry Volume 48, No. 8 (1965) pages 1342; US 3,978,185, US 3,795,571; 3,811,957). Stretching of nonwoven webs is described in U.S. 3,772,417, US 4,048,364, US 4,223,059, 3,949,127, US 4,276,336, US 5,296,289, US 4,443,513 and EP 0 882 147. However, none of these disclosures relates to the causal connection of stretching of a nonwoven web and imparting elastic properties.

Thermally bonded nonwoven webs are conventionally used for the mass production of disposable sanitary protection products such as adult and infant diapers or sanitary napkins, medical products such as masks, operating gowns, head covers or operating drapes; protective work-wear such as coveralls, head covers and masks; and personal use items such as underwear. A major deficiency of nonwoven webs is their lack of elasticity or stretch and conformability. Since conventional thermally bonded nonwoven webs do not have sufficient elastic properties, products containing such nonwoven webs which require elastic properties conventionally further contain latex bands for fastening and fitting. However, proper adjustment of latex straps is difficult to achieve whereby a fit is usually observed which is either too loose or too tight. Moreover, latex straps are allergenic and irritating to the skin to some degree. Additionally, the use of latex and rubber components in huge volume for disposable products has raised serious environmental concerns in view of toxic waste generation such as dioxins and other harmful emissions in the waste incineration process.

Attempts were made in the prior art to provide nonwoven webs having elastic properties. In one approach, elastomers are incorporated into nonwoven webs as films, bands, or threads of natural or synthetic rubber whereby full-web elasticity in two directions is achieved. However, nonwoven webs based on elastomers lack dimensional stability in at least one direction whereby it is difficult to handle such webs in automated manufacturing processes. Moreover, nonwoven webs based on elastomeric fibers are expensive. Therefore, the use of elastomeric fibers poses inherent problems which render them unsuitable for the mass production of disposable products.

An alternative approach for imparting elasticity to a nonwoven web relates to the so-called thermo-mechanical treatments. Thermo-mechanical treatments for imparting elasticity to a nonwoven web are described in US 5,244,482 and EP 0 844 323. Accordingly, a thermally bonded nonwoven precursor web is subjected to a stretching treatment at an elevated temperature in one direction (machine direction) whereby the width of the precursor web shrinks in perpendicular direction (cross direction) resulting in a certain elasticity in cross direction while maintaining non-elastic properties in machine direction. The anisotropic elasticity combining dimensional stability in machine direction and elastic properties in the cross direction facilitates the use of such webs in automated manufacturing processes.

U.S. 5,244,482 disclosed a process for the preparation of a filter material, wherein very high strain rates of at least 2500%/min are used to laterally consolidate the precursor web with resultant width of less than 80% of the precursor. The very high strain rates are shown to change the morphology of the nonwoven web, reduce the pore size and narrow the pore size distribution. Although a degree of elasticity is created, the elastic modulus is low (70% recovery at 50% elongation, 40% recovery at 100% elongation). We already learn a low draw ratio will not make a high stretchy resultant web. The required strain rates mean in a continuous process, that a high draw ratio with a high processing speed of from 1000 to 4000 m/min are unlikely to be achieved in practice. Moreover, the resultant fabrics is stiff whereby mass production of disposable products based on the material of U.S. 5,244,482 is not possible.

EP 0 844 323 discloses a process wherein a nonwoven web is stretched under low strain rates of from 350 to 950 %/min and carefully controlled thermal process conditions for creating a degree of elasticity (85% recovery at 50% elongation) within the precursor web. However, the

degree of elasticity of the resultant webs turned out to be still insufficient for meeting the standards required for commercially successful applications. Moreover, although the process of EP 0 844 323 may be carried out in a continuous mode, the maximum process speed attainable is well below 100 m/min whereby mass production cannot be considered economical.

DISCLOSURE OF THE INVENTION

It is the problem of the present invention to overcome the drawbacks of the prior art and to provide a cost effective process of mass producing an elastic thermally bonded nonwoven web having elastic properties in cross direction with high stretchability and recovery.

It is a further problem of the invention to provide a process wherein the processing speed is at least 100 m/min, preferably in a range of from 200 to 400 m/min.

It is a further problem of the invention to provide a novel elastic nonwoven web having high stretchability in cross direction of over 100% with recovery of more than 70%. Moreover, it is a further problem of the invention to provide a novel elastic nonwoven web having high stretchability in cross direction of over 150% with recovery of more than 60%.

It is a further problem of the present invention to provide novel products containing the elastic nonwoven web of the present invention.

These problems are solved according to the claims. Accordingly, the present invention provides a process of preparing an elastic thermally bonded nonwoven web, whereby the process is characterized by the following steps:

- (i) providing a thermally bonded nonwoven precursor web containing thermoplastic fibers,
- (ii) subjecting the precursor web of step (i) to a drawing treatment in a machine direction at a drawing rate of from 45 to 70 %, and
a strain rate within a range of from 1000 to 2400 %/min

at a temperature between the softening point and the melting point of the fibers for preparing the elastic thermally bonded nonwoven web.

For the drawing treatment, the web is heated to a temperature above the softening point where a thermoplastic fiber loses its room temperature modulus and becomes soft, viscous and transformable.

The present invention is based on the recognition that control of the strain rate alone is insufficient for imparting superior elastic properties to a thermally bonded nonwoven precursor web in a thermo-mechanical treatment. The present invention is further based on the recognition that control of a further measure is essential for obtaining superior elastic properties. The present invention identifies the control of the drawing rate in combination with the control of the strain rate as essential measures for imparting superior elastic properties. The drawing ratio was found to be causal for shrinking the web width and for creating the stretchability and elasticity. A low drawing rate insufficiently reduces the width of the precursor web and imparts less stretchability and elasticity to the finished web. Finally, the present invention is based on the recognition that the control of a combination of the drawing rate of from 45 to 70 %, and a strain rate within a range of from 1000 to 2400 %/min provides superior elastic properties, notably with nonwoven precursor webs containing polypropylene. Accordingly, elastic properties imparted by a thermo-mechanical treatment to a thermally bonded nonwoven precursor web may be dramatically improved whereby the nonwoven webs show an elasticity in the cross direction of at least 70% recovery from a 100% elongation, and at least 60% recovery from a 150% elongation. Moreover, the nonwoven webs provide unidirectional elasticity wherein the ratio of elongation at break in cross direction to the elongation at break in machine direction is at least 800%. Thermally bonded nonwoven web having such elastic properties were unknown prior to the present invention.

BRIEF DESCRIPTION OF THE FIGURES

Figure 1 shows schematically an apparatus for carrying out the process of the invention.

Figure 2 shows a schematic side view of an apparatus for carrying out the process of the invention.

Figure 3 illustrates shows a schematic side view of a further embodiment of an apparatus for carrying out the process of the present invention.

Figure 4 is a graph showing the relationship of the present invention to U.S. 5,244,482 and EP 0 844 323 with regard to the parameters of the width reduction and the strain rate. The present invention provides a window of opportunity for increasing the process speed and improving the elastic properties, which only exists in the claimed area as shown by the examples.

DETAILED DESCRIPTION OF THE INVENTION

Figure 1 shows schematically an apparatus for carrying out the process of the invention. The apparatus comprises an unwinding roll (10) and a winding roll (30) provided essentially in parallel orientation for allowing transfer of a web (1) from the unwinding roll (10) to the winding roll (30). The winding roll (10) preferably has a width corresponding to the width (a) of the precursor web prior to the stretching treatment. The winding roll preferably has a width corresponding to the width (b) of the web after the drawing treatment. Since the width of the web (1) decreases during the drawing treatment, the unwinding roll (10) has a greater width than the winding roll (30). The unwinding roll (10) and the winding roll (30) may be rotated around their longitudinal axis. The rotation may be controlled independently for the unwinding roll (10) and the winding roll (30). The unwinding roll supports a nonwoven web (1). The nonwoven web extends from the unwinding roll (10) to the winding roll (30) through a heating means (20) such as an oven. Preferably, a first S-wrap (15) comprising guiding roll (151) and guiding roll (152) is provided between the unwinding roll (10) and the heating means (30). Moreover, a second S-wrap (25) comprising guiding roll (251) and guiding roll (252) is provided between the heating means (20) and the winding roll (30). The nonwoven web supported by the unwinding roll (10) corresponds to a precursor web. The precursor web extends from the unwinding roll (10) in machine direction optionally passing S-wrap (15) towards the entrance of the heating means (20). The nonwoven web enters the heating means (20) and extends through the heating means towards the exit of the heating means. Downstream from the heating means, the nonwoven web extends optionally via S-wrap (25) to the winding roll (30). The heating means (20) is provided for heating the nonwoven web to a temperature between the softening point of the thermoplastic fibers of the web and the melting point of the thermoplastic fibers. The S-wraps (15) and (25) are provided for better controlling the movement of the nonwoven web.

Now, the process of the invention will be illustrated based on the apparatus shown in Figure 1. Accordingly, an elastic thermally bonded nonwoven web is prepared by providing a thermally bonded nonwoven precursor web containing thermoplastic fibers whereby said precursor web is supported by unwinding roll (10). Unwinding roll (10) is rotated around its longitudinal axis whereby the precursor web leaves unwinding roll (10) in machine direction along arrow (MD) at a speed A. The precursor web travels *via* S-wrap (15) into the heating means (20), through the heating means and from the exit of the heating means *via* S-wrap (25) to the winding roll (30). Winding roll (30) is driven at a speed higher than the unwinding speed A by a factor of $(1+X\%)$. The factor $(1+X\%)$ determines the drawing rate of the nonwoven web in the process of the present invention. According to the invention, the precursor web is subjected to a drawing treatment in a machine direction at a drawing rate of from 45 to 70 %, and a strain rate with a range of from 1000 to 2400 %/min at a temperature between the softening point and the melting point of the fibers in order to allow a consolidation of the fiber structure and a decrease of the width of the nonwoven web. As a result of the drawing treatment, the width of the web decreases in the cross direction (CD). Preferably, the machinery for carrying out the process of the invention is constructed for commercial capacity with an unwinder roll and a winding roll(s) installed in a distance of from 4 to 12 m, preferably about 6 to 10 m, specifically 8 m, and a heating device installed in between. The unwinder advantageously runs at commercial speed of more than 100m/min and up to 400m/min, preferably at least 150 m/min and up to 250 m/min, and a draw ratio of 45% to 70 % is created by increasing the speed of the winding roll. The strain rates is adjusted to 1000 to 2400 %/min, preferably 1200 to 2200%/min. Preferably, the drawing treatment in step (i) comprises introducing the thermally bonded nonwoven web into a heating means for heating the web to a temperature between the softening point and the melting point of the fibers. The drawn web is preferably cooled after the drawing treatment and prior to winding on storage roll.

The web used in the process of the invention preferably contains polypropylene fibers. The amount of the polypropylene fibers in the web is preferably at least 30 % by weight. The web may contain further fibers, such as thermoplastic fibers or cellulosic fibers. In a specific embodiment, the web consists of polypropylene fibers. The nonwoven web of the present invention has anisotropic elasticity properties, preferably a ratio of elongation at break in cross direction to the elongation at break in machine direction of at least 800 %. The nonwoven web may be a spunbonded web, a melt blown web or a carded thermally bonded nonwoven web, or

the nonwoven web may be a laminate containing two or more of the above mentioned nonwoven webs or the web may be a laminates of the above mentioned nonwoven webs and a thermoplastic film. Several kinds of thermally bonded nonwoven webs including carder, spunbond, SMS and SMMS from different producers have been processed and the resultant webs exhibit high stretchability with high recovery in the cross-direction. The cross-direction-only elasticity of these webs truly frees the nonwoven product converting from the need of sewing latex straps in their conventional methods, and the converted products provide sensational easy-fit and stressless comfort to wearer.

The webs of this invention may be a multilayer laminate. An example of a multilayer laminate is an embodiment wherein some of the layers are spunbond and some meltblown such as a spunbond-meltblown-spunbond (SMS) laminate as disclosed in US 5,169,706. SMMS is the laminate of Spunbond-meltblown -meltblown- spunbond. Such a laminate may be made by sequentially depositing onto a moving forming belt first a spunbond fabric layer, then a meltblown fabric layer and last another spunbond layer and then bonding the laminate in a spotbinding device. Alternatively, one or more of the fabric layers may be made individually, collected in rolls, and combined in a separate bonding step.

The web of carded or thermalbond described in this invention is obtainable by mixing and carding staple fibers for formed a mat then bonded with a spotbonding method.

Preferably, the process of the invention is carried out continuously. The drawing treatment in step (i) of the continuous process according to the invention may comprise unwinding the thermally bonded nonwoven web into a first variable tension means which feeds said web into a web heating means for heating the web to a temperature between the softening point and the melting point of the fibers, followed by continuously stretching the heated web lengthwise in the machine direction, cooling the web and collecting the cooled web. The nonwoven web containing thermoplastic fibers can be softened in the range of temperature prior to melting. In the softened states, a mechanical force can be applied to the web to change its morphology and properties. After the drawing treatment and the cooling below the softening temperature, the finished web exhibits different characteristics from its precursor.

Figure 2 shows a schematic side view of an alternative apparatus lacking S-wraps. The apparatus comprises one unwinder and a winder and an oven in between to apply constant heat to a fabric that runs through. The transformation of the nonwoven web is carried out within the distance between the unwinder and winder (D). The strain rate (%/t) is generally described as a piece of fabric being drawn and extended certain (X) percentage in a period of time. The extension percentage can be achieved by the speed ratio of winder to unwinder, and the time period of fabric run through can be calculated by dividing D over the average of unwinder speed (A) and winder speed $[(1+X\%) A]$. Speed A is generally expressed in m/ min as :

$$X\% / \{D / [A + (1+X\%) A] / 2\} = X\% / \{2D / [A + (1+X\%) A]\} = \{X\% \times [A + (1+X\%) A]\} / 2D$$

Figure 3 illustrates shows a schematic view of a further embodiment of an apparatus for carrying out the process of the present invention. The apparatus includes one S-wrap (15) after unwinder and one S-wrap (25) before winder for stabilizing the fabric feeding through. The transformation of the nonwoven web is carried out within the distance (D) between these two S-wraps. The extension percentage can be achieved by the speed ratio of S-wrap 2 to S-wrap 1, and the time period of fabric run through can be calculated by dividing D over the average of S-wrap 1 speed (A) and S-wrap 2 speed $[(1+X\%) A]$.

The present invention also provides an elastic thermally bonded nonwoven web containing polypropylene fibers, which is obtained or obtainable by the process of the present invention. The web elasticity is defined by measuring the variations of a 5-cm wide and 10cm long strip along the longitudinal axis as follows:

$$(\text{stretched length} - \text{recovered length}) / (\text{stretched length} - \text{original length}).$$

The elastic thermally bonded nonwoven web preferably has an elasticity in the cross direction of at least 70% recovery from a 100% elongation, and at least 60% recovery from a 150% elongation. In a specific embodiment, the elastic thermally bonded nonwoven web is laminated on an elastomeric film.

The present invention also provides a use of the elastic nonwoven web for the preparation of a disposable sanitary protection product, a medical product, a protective work-wear or a personal use item. The present invention also provides a product containing an elastic

nonwoven web of the invention. The product may be is a disposable sanitary protection product, a medical product, a protective work-wear or and a personal use item. The disposable product may be an adult or infant diaper, or a sanitary napkin. The medical product may be a mask, an operating gown, a head cover, or an operating drape. The protective work-wear may be a coverall, a head cover or mask. The personal use item may be underwear.

The process of the invention does not use expensive, allergenic and environmentally unsafe elastomeric fibers for imparting elasticity.

EXAMPLES

Terminology::

The basis weight of nonwoven webs is usually expressed in minigram of material per square meter (gsm).

The softening point is the temperature where a thermoplastic fiber loses its room temperature modulus and becomes soft, viscous and transformable to applied force.

As used herein the term "spunbond" refers to the webs formed by small diameter fibers which are formed by extruding molten thermoplastic material as filaments from a plurality of fine, usually circular capillaries of a spinneret with the diameter of the extruded filaments then being rapidly reduced as by, for example, in US 4,340,563 and US 3,692,618, US 3,802,817, US 3,338,992 and 3,341,394, US 3,502,763, US 3,502,538, and US 3,542,615. Spunbond fibers are generally not tacky when they are deposited onto a collecting surface. Spunbond fibers are generally continuous and have average diameters (from a sample of at least ten fibers) larger than 7 microns, more particularly, between about 10 and 30 microns.

Tensile test: The tensile test is a measure of breaking strength and elongation or strain of a fabric when subjected to unidirectional stress. This test is known in the art and conforms to the specifications of Method D5034 of the American Standard Test Methods. The results are expressed in kilograms to break and percent stretch before breakage. Higher numbers indicate a stronger, more stretchable fabric. The term "elongation" means the increase in length of a specimen during a tensile test. Values for grab tensile strength and grab elongation are

obtained using a specified width of fabric, usually 3 cm, clamp width and a constant rate of extension. The sample is wider than the clamp to give results representative of effective strength of fibers in the clamped width combined with additional strength contributed by adjacent fibers in the fabric.

Example 1

17gsm SMS nonwoven fabrics were processed over 8-meters distance between unwinder and winder to show the width reduction under different strain rates and conditions further specified in Table 1. As shown by Table 1, a draw rate over 45% was required to reduce the width by 50%. Upon increase of the speed by 10m/min, it was required to increase the draw ratio by about 1.5% to maintain the width reduction.

Table 1

Unwinding Speed	Draw Ratio	Winding Speed	Strain Rate	Width Reducing
m/min	%	m/min	% / min	%
150	40	210	900	45.4
	45	218	1035	52.3
	50	225	1172	57.7
	55	233	1317	61.5
	60	240	1463	62.2
	65	250	1625	63.1
200	40	280	1200	43.4
	45	290	1378	51.8
	50	300	1563	55.7
	55	310	1753	58.5
	60	320	1950	60.6
	65	330	2153	61.8
250	40	350	1500	41.4
	45	363	1724	50.7
	50	375	1953	53.6
	55	388	2193	56.3
	60	400	2438	57.9
	65	413	NA	Broke webs

Example 2

Different basic weights of SMS precursor webs were processed at unwinding speed of 200m/min and with 50 % draw rate. The results shown in Table 2 demonstrate that the draw ratio made similar width reductions to precursor webs with different basic weights.

Table 2.

Precursor Basic Weight	Draw Ratio	Strain Rate	Width Reduction	Finished Basic weight
g/cm ²	%	%/min	%	g/cm ²
16.7	50	1563	56.8	26.4
26.6	50	1563	55.3	39.8
35.4	50	1563	57.1	51.3
52.3	50	1563	55.4	68.6

Example 3

Nonwoven webs of Spunbond (S), Carded (C) SMS and SMMS were treated at 200 m/min unwinding speed with 30 to 60% draw ratios. It was shown in Table 3 that the draw ratio made the length extension and the width reduction in similar pattern of 30-60% with different thermally bonded nonwoven webs and at least 45% draw ratio was required to reduce 50% of the precursor width.

Table 3

Precursor	Basic weight	Draw Ratio	Strain Rates	Finished Basic weight	Length Extension	Width Reducing
	g/cm ²	%	%/min	g/cm ²	%	%
S	12.7	30	750	15.5	1.26	34.6
	12.7	40	1000	17.4	1.34	45.0
	12.7	45	1125	18.1	1.37	50.6
	12.7	50	1250	19.2	1.40	52.4
	12.7	60	1500	21.7	1.53	59.8
S	25.6	30	750	28.3	1.28	32.3
	25.6	40	1000	33.6	1.37	43.8
	25.6	45	1125	34.7	1.40	50.1
	25.6	50	1250	36.5	1.44	50.6
	25.6	60	1500	40.8	1.56	58.1
C	22.6	30	750	31.4	1.20	38.1
	22.6	40	1000	33.9	1.29	49.6

	22.6	45	1125	35.2	1.32	52.2
	22.6	50	1250	36.7	1.36	55.8
	22.6	60	1500	41.3	1.45	61.8
C	44.3	30	750	56.9	1.21	37.0
	44.3	40	1000	67.6	1.26	49.1
	44.3	45	1125	69.2	1.30	52.7
	44.3	50	1250	70.3	1.34	54.2
	44.3	60	1500	74.9	1.44	60.9
SMS	15.2	30	750	20.9	1.18	37.7
	15.2	40	1000	22.6	1.24	48.3
	15.2	45	1125	23.4	1.31	51.5
	15.2	50	1250	24.1	1.36	53.4
	15.2	60	1500	26.3	1.46	57.8
SMS	41.7	30	750	54.4	1.15	35.5
	41.7	40	1000	62.5	1.20	46.1
	41.7	45	1125	65.2	1.31	52.2
	41.7	50	1250	67.2	1.42	56.4
	41.7	60	1500	72.6	1.51	62.3
SMMS	17.1	30	750	20.5	1.17	30.7
	17.1	40	1000	23.8	1.25	42.5
	17.1	45	1125	24.4	1.31	50.3
	17.1	50	1250	25.6	1.37	52.2
	17.1	60	1500	29.1	1.48	59.4
SMMS	50.6	30	750	58.7	1.26	32.9
	50.6	40	1000	68.8	1.34	46.2
	50.6	45	1125	70.4	1.38	50.1
	50.6	50	1250	72.8	1.41	51.6
	50.6	60	1500	78.3	1.52	58.3

Example 4

Spunbond 35gsm, Carded 45gsm and SMMS 25gsm were used as precursor for processing under different draw ratio to obtain the width reduction from 30% to 60%. The results are shown in Table 4. The elasticities were measured from 50%, 100% and 150% elongation respectively. The resultant webs with width reduction less than 40% are most unlikely to be extended for more than 100% and obtained good recovery for over 50%. In contrast, the resultant webs with width reduction over 50% showed recovery more than 70% at 100% elongation and more than 60% at 150% elongation.

Table 4

	Width Reduction	Strain Rate	Elongation at Break	Recovery from 50% elongation	Recovery from 100% elongation	Recovery from 150% elongation
	%	%/min	%	%	%	%
Spunbond 43gsm	30	720	89	72	NA	NA
Spunbond 47gsm	40	1050	104	88	NA	NA
Spunbond 52gsm	50	1380	184	>95	78	63
Spunbond 62gsm	60	1710	237	>95	86	73
Carded 54gsm	30	690	104	75	NA	NA
Carded 60gsm	40	1020	129	90	24	NA
Carded 67gsm	50	1350	203	>95	73	65
Carded 78gsm	60	1680	248	>95	80	74
SMMS 28gsm	30	780	93	76	NA	NA
SMMS 31gsm	40	1080	115	85	NA	NA
SMMS 36gsm	50	1410	197	>95	77	66
SMMS 40gsm	60	1790	226	>95	86	77

Example 5

The results shown in Table 5 further confirmed the high elastic recovery rates of the webs over five stretches for 100% (A) and 150% (B) elongations. The unique high ratio (1000 – 1400%) of CD/MD elongation at break is also shown..

Table 5.

Finished webs		Spunbond 38gsm	Carded 40gsm	SMS 65gsm	SMMS 70gsm
Strain Rate Applied	%/min	1410	1410	1410	1410
Width reduction	%	52	54	53	50
Elongation at Break (+%)	MD	14.6	15	15.3	16.3
	CD	178	210	190	188
CD/MD Elongation Ratio	%	1220	1400	1240	1150

Recovery Ratio for 5 repeated stretches with 100% (A) and 150% (B) elongation	Elongations	A	B	A	B	A	B	A	B
	%	83	68	80	66	78	66	76	63
		75	62	74	61	73	57	71	55
		73	60	71	58	70	54	67	50
		71	57	69	55	68	52	66	47
		70	55	67	52	66	51	63	45

Example 6

The stretchability and recovery were tested with 5-cm strips of treated SMS webs with the claimed high and low limits of strain rates. The results are shown in Table 6. The unique characteristics of cross direction (CD) width reduction, elongation at break, CD/MD elongation ratio and recovery at 100% elongation were measured.

Table 6.

Precursor Basic Weight	(g/m ²)	16.4	16.4	25.6	25.6	34.7	34.7	51.3	51.3
unwinding Speed	m/min	150	250	150	250	150	250	150	250
Strain Rate Applied	%/min	1035	2438	1035	2438	1035	2438	1035	2438
Finished Basic Weight	(g/m ²)	23.7	28.3	35.7	42.8	47.6	56.4	64.4	76.9
Width reduction	%	50.7	58.8	52.1	60.6	50.4	61.2	53.2	62.4
Elongation (+%)	MD	19.4	16.7	18.7	15.3	21.4	16.9	20.8	16.3
	CD	162	214	167	223	176	231	184	243
CD/MD Elongation Ratio	%	835	1280	890	1458	822	1367	885	1490
Recovery % for 10 stretches at 100% elongation	%	76	83	76	82	73	80	72	77

		72	78	72	76	68	74	68	71
		70	76	70	74	66	73	65	68
		70	74	70	73	63	73	62	67
		69	73	68	72	62	71	60	66
		69	73	67	71	59	70	58	65
		68	72	65	70	59	69	59	64
		68	72	65	68	59	67	55	64
		67	72	64	68	58	65	55	63
		67	70	64	68	57	65	55	63

The strain rate is calculated by the percentage of increasing length within the time period of time that makes such increase. The percentage of increasing length is the draw ratio, which is carried out by increasing the winding speed over the unwinder. The time period of making such length increasing is calculated by dividing the distance between the unwinder and the wining roll with the speed of the web passing through, and that speed is an average of unwinder speed and winding speed.

For example, the present invention requires at least 45% draw ratio in a distance of 8 meters between unwinder and winding roll and with a minimal speed of 150m/min for unwinder, to reduce the width of the precursor web by 50% and become the elastic nonwoven web of the invention. The strain rate in the low limit of the present invention is calculated as:

$$45\% / \{8\text{m} / [150\text{m}/\text{min} + (150\text{m}/\text{min} \times 1.45)] / 2\} = 1034\% / \text{min}$$

wherein

- (1) 45% is the draw ratio;
- (2) 8 m is the distance between unwinder and winding roll that the drawing being created;
- (3) 150m/min is the unwinder speed;
- (4) $150\text{m}/\text{min} \times 1.45 = 217.5\text{m}/\text{min}$ is the winding roll speed;
- (5) $[150\text{m}/\text{min} + (150\text{m}/\text{min} \times 1.45)] / 2 = 183.75 \text{ m}/\text{min}$ is the averaged travelling speed of the web through the drawing;
- (6) $8\text{m} / [150\text{m}/\text{min} + (150\text{m}/\text{min} \times 1.45)] / 2 = 0.04354 \text{ minute}$ is the time that the drawing happened

The 0.04354 minutes (2.61 second) processing time is essential also for the web to pick up the heat and raise its temperature from 25C to 125°C for softening.

The higher strain rates can be obtained by processing at high speed and high draw ratio. However, tests in the 8-meter processing distance had revealed that it would be impractical and break the commonly available nonwoven web that containing thermally bonded polypropylene fibers at a draw ratio of over 70% and a winding speed over 500m/min. In the case, the strain rate was 3500 %/min and less than 1.2 second for web to be heated.

Any higher draw ratio or higher speed for higher strain rates as the previous US 5,244,482 inventions described is considered incredible and impossible to be achieved especially for a continuous processing with the current commercial apparatus and on polypropylene nonwoven web. A temperature very close to the melting point was probably used in combination with a very high strain, whereby the resulting web has a width reduction of 80% of the precursor web, but an elongation of only below 120%. Such a fabric would be of little commercial value due to the stiffness, low degree of elasticity (70% recovery at 60% elongation) and very narrow width (if a 420 cm maximum width of a precursor web is used, the resulting web would be only 84 cm in width or less). Additionally, U.S. 5,244,482 places many limitations on selecting the precursor webs by the physical properties as to crystallinity, thermoplastic fiber content, fiber diameter, random fiber deposition, isotropic tensile properties and low tensile elongation to break. As a matter of fact, there is no commercial application of this art since it was disclosed.

The best result is obtained according to the present invention at 50% draw rate with feeding speed of 200m/min to make the strain rate at 1600%/min. The average strain rate of the best mode claimed by US 5,244,482 was 4750%/min, and to attain it with an apparatus as shown in figure 1 and a 50% drawing rate, the feeding speed would have to be as high as 608m/min. As tested in an apparatus according to figure 1 with the 50% draw rate and with commercially available nonwoven webs, the feeding speed cannot be increased over 400m/min without breaking the web. As a matter of fact, the maximal feeding speed stated in the experiment of US 5,244,482 was only 122m/min (400f/min), then for reaching the best strain rate, the draw rate has to be as high as 250%. Accordingly, US 5,244,482 is limited to special precursor webs with strict limitations in the properties of crystallinity, fiber diameter, random fiber deposition, isotropic tensile properties, and low tensile elongation to break.

EP 0 844 323 on the other hand describe a method of using low strain rate that between 350% and 950% per min at speed below 100m/min. EP 0 844 323 describes clearly that the width reduction of the precursor web was between 30-40% and the finished web has an elasticity for 85% recovery from 50% elongation. Accordingly, the draw ratio would be around 35% or less and that theoretically it should not be possible to stretch the finished web more than 66.7% (100/60) to over the width of its precursor. EP 0 844 323 describes the treatment with multiple sets of drawing rolls to make the accumulated strain rate typically below 950% but above 350 % per minute. In fact, the more sections of drawing rolls are present, the lower the processing speed has to be adjusted to meet the claimed low strain rate range. For example, assuming with the description of EP 0 844 323 a minimal two (2) sets drawing rolls over 8 meters distance and 35% drawing ratio equally made in two sets to make the claimed highest 950%/min strain rate, the maximal feeding speed (x) can be calculated as:

$$17.5\% / [4m/(x + 1.175x)/2] + 17.5\% / \{4m/[1.175x + 1.175 (1.175x)]/2\} \leq 950\%/min$$

$$\begin{aligned} \text{Equal: } [17.5\% (2.175x) / 8m] + [17.5\% (2.556x) / 8m] &= 950\%/min \\ 17.5\% (4.731x) &= 7600 \% m /min \\ x &= 91.8 m /min \end{aligned}$$

Processing under such low speed would raise the cost and has little commercial value to meet the applications of mass quantity and low-cost disposable nonwoven products, but any higher processing speed would make the strain rate over its claimed limit. More sets of drawing rolls or lower strain rates would further lower the processing speed. Additionally, the low draw ratio would surely not consolidate the web enough to make the high elasticity as the web resulted from the present invention.

Most importantly, the strain rate is not appropriate to be used to describe a process without specifying the two variables, the draw ratio, and the rate of the processing (the processing distance over the processing speed), since the same strain rates can be obtained with different combinations of parameters in the equation. Both U.S. 5,244,482 and EP 0 844 323 use the strain rate as the only parameter for defining their methods but without clarifying the rate of the processing and so there is no way of knowing how to come up the numbers of

their strain rates. Still, there is no conflict of those previous descriptions with the present invention in the strain rates. Hassenboehler's invention claimed their method at strain rate at least 2500% per min, and Ward's invention claimed the range between 350% to 950% per min. The present invention operates in the range of 1000% to 2400% per min as shown by figure 4.

05. Dez. 2003

Claims

1. A process of preparing an elastic thermally bonded nonwoven web, whereby the process is characterized by the following steps:
 - (i) providing a thermally bonded nonwoven precursor web containing thermoplastic fibers,
 - (ii) subjecting the precursor web of step (i) to a drawing treatment in a machine direction at a drawing rate of from 45 to 70 %, and a strain rate within a range of from 1000 to 2400 %/min at a temperature between the softening point and the melting point of the fibers for preparing the elastic thermally bonded nonwoven web.
2. The process according to claim 1, wherein the processing speed is at least 100 m/min, preferably in a range of from 200 to 400 m/min.
3. The process according to claim 1 or 2, wherein the drawing treatment in step (i) comprises introducing the thermally bonded nonwoven precursor web into a heating means for heating the web to a temperature between the softening point and the melting point of the fibers.
4. The process of any one of claims 1 to 3, which further comprises the step of cooling the web after the drawing treatment.
5. The process according to any one of the preceding claims, wherein the precursor web contains polypropylene fibers.
6. The process according to claim 5, wherein the polypropylene fibers are contained in an amount of at least 30% by weight.
7. The process according to any one of the preceding claims, wherein the precursor web contains cellulosic fibers.

8. The process according to claim 1, wherein the precursor web consists of polypropylene fibers.
9. The process according to any one of the preceding claims, wherein the elastic nonwoven web has anisotropic elasticity properties.
10. The process of claim 9, wherein the ratio of elongation at break in machine cross direction to the elongation at break in machine direction is at least 800%.
11. The process of any one of the preceding claims, wherein said said nonwoven precursor web is a spunbonded web.
12. The process of any one of the preceding claims, wherein nonwoven precursor web is a melt blown web.
13. The process works of any one of the preceding claims, wherein said said nonwoven precursor web is a carded thermally bonded nonwoven web.
14. The process of any one of the preceding claims, wherein said nonwoven web is a laminate containing two or more of the nonwoven webs according to any one of claims 11 o 13, or a laminate of the nonwoven webs according to any one of claims 11 o 13 and a thermoplastic film.
15. The process according to any one of the preceding claims, wherein said thermally bonded nonwoven web is a blend of thermoplastic fibers and cellulosic fibers wherein said web contains at least 30% thermoplastic fibers.
16. The process according to any one of the preceding claims, wherein the the process is carried out continuously.
17. The continuous process according to claim 16, wherein the drawing treatment in step (i) comprises unwinding the thermally bonded nonwoven web into a first variable tension means which feeds said web into a web heating means for heating the web to

a temperature between the softening point and the melting point of the fibers, followed by continuously stretching the heated web lengthwise in the machine direction, cooling the web and collecting the cooled web.

18. A thermo-mechanical method for treating a nonwoven web according to any one of the previous claims which comprises:
 - a. providing a thermally bonded polypropylene nonwoven web of carded, spunbond, SMS and SMMS as precursor web;
 - b. provide an unwinder roll and the winding roll in a distance of 6-10 meters.
 - c. continuously feeding the precursor web from the unwinder roll to the winding roll at a speed in a range of from 150m/min to 400m/min;
 - d. heating the precursor web at a temperature between the softening temperature and melting temperature of the thermoplastic polypropylene;
 - e. drawing the heated web by increasing the speed of winding roll over the unwinder at least 45% and to 70%, to thereby reduce the width of the web by 50% to 65 % whereby the
 - f. strain rates are within the range of 1000% to 2400% /min.
19. The process according to claim 18, wherein the unwinding roll is a pair of pin-rolls to make a S-wrap for creating the draw ratio and release the finished web to the winder.
20. The process according to claim 18, wherein the precursor web is a single layer or multiple layers construction that are thermally bonded or laminated.
21. A elastic thermally bonded nonwoven web containing polypropylene fibers obtained or obtainable by the process of any one of claims 1 to 20.
22. The elastic thermally bonded nonwoven web according to claim 21 which has an elasticity in the cross direction of
 - at least 70% recovery from a 100% elongation, and
 - at least 60% recovery from a 150% elongation.

23. An elastic nonwoven web according to claim 21, made from a nonwoven precursor of carded, spunbond, SMS, and SMMS comprising polypropylene thermoplastic fibers and being heated and drawn in longitudinal direction over a 6-10 meters distance at speed range of 150m/min to 400m/min to reduce 50% to 65 % the width of its precursor, wherein the drawing is made by feeding the web through a heating device installed between the unwinding and winding rolls to heat up the web in the temperature between the softening temperature and melting temperature of the thermoplastic fibers and by spontaneously increasing the speed of winding roll over unwinder at least 45% to maintain the strain rate in the range of 1000% to 2400% per minute, whereby the elastic nonwoven web is characterized by the elasticity of at least 70% recovery from a 100% elongation, or 60% recovery from a 150% elongation, in the cross direction.
24. The elastic nonwoven web of claim 23 wherein the precursor web is composed of co-filament fibers, or the mix of mono and co-filaments.
25. The elastic nonwoven web of claim 23 wherein the core of the co-filaments is composed of different thermoplastics of sheath.
26. An elastic laminate comprising:
(a) the elastic nonwoven web of claim 21; and
(b) a stretchable substrate bonded to the elastic nonwoven web.
27. The elastic nonwoven laminate of claim 26 wherein the substrate is an elastomeric layer.
28. The elastic nonwoven web of claim 26 or 27 wherein the substrate is a film.
29. Use of the elastic nonwoven web according to any one of claims 21 to 28 for the preparation of a disposable sanitary protection product, a medical product, a protective work-wear or a personal use item.

30. The use according to claim 29, wherein the disposable product is an adult or infant diaper, or a sanitary napkin.
31. The use according to claim 29, wherein the medical product is a mask, an operating gown, a head cover, or an operating drape.
32. The use according to claim 29, wherein the protective work-wear is a coverall, a head cover or mask.
33. The use according to claim 29, wherein the personal use item is underwear.
34. Product containing an elastic nonwoven web according to any one of claims 21 to 28.
35. The product according claim 34, which is a disposable sanitary protection product, a medical product, a protective work-wear or and a personal use item.
36. The product according claim 35, wherein the disposable product is an adult or infant diaper, or a sanitary napkin.
37. The product according claim 35, wherein the medical product is a mask, an operating gown, a head cover, or an operating drape.
38. The product according claim 35, wherein the protective work-wear is a coverall, a head cover or mask.
39. The product according claim 35, wherein the personal use item is underwear.

05. Dez. 2003

ABSTRACT

A process of preparing an elastic thermally bonded nonwoven web, whereby the process is characterized by the following steps:

- (i) providing a thermally bonded nonwoven precursor web containing thermoplastic fibers,
- (ii) subjecting the precursor web of step (i) to a drawing treatment in a machine direction at a drawing rate of from 45 to 70 %, and
a strain rate within a range of from 1000 to 2400 %/min
at a temperature between the softening point and the melting point of the fibers for preparing the elastic thermally bonded nonwoven web.

Fig. 1




Fig.2




Fig.3




Fig. 4

